

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
19 July 2001 (19.07.2001)

PCT

(10) International Publication Number
WO 01/51536 A1

(51) International Patent Classification⁷: **C08G 18/22**,
18/64, C07F 7/00, B01J 31/22

DL3 9AH (GB). **RIDLAND, John** [GB/GB]; 12 Oatlands
Way, Durham, County Durham DH1 5GL (GB).

(21) International Application Number: PCT/GB00/04853

(74) Agents: **GIBSON, Sara, Hillary, Margaret** et al.; Syntex
Intellectual Property Dept., Belasis Avenue, P.O. Box 1,
Billingham, Cleveland TS23 1LB (GB).

(22) International Filing Date:
18 December 2000 (18.12.2000)

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0000569.4 12 January 2000 (12.01.2000) GB
60/211,910 16 June 2000 (16.06.2000) US

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **IM-
PERIAL CHEMICAL INDUSTRIES PLC** [GB/GB];
Imperial Chemical House, Millbank, London SW1P 3JF
(GB).

Published:
— with international search report

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **PARTRIDGE, Mar-
tin, Graham** [GB/GB]; 26 Pinewood Road, Eaglescliffe,
Stockton on Tees, Cleveland TS16 0AJ (GB). **STENGEL,
Bruno, Frederic** [FR/GB]; 79 Staindrop Road, Darlington

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: ORGANOMETALLIC COMPOSITIONS

(57) Abstract: An organometallic composition is described which comprises a complex of at least one orthoester of a metal having a formula $M(ROAcAc)_x(OR')_y$, in which M is selected from the group consisting of titanium, zirconium and hafnium; ROAcAc denotes an ester of an alcohol ROH, in which R comprises an (optionally substituted) C_{1-30} cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof, with acetoacetic acid; OR' is the residue of an alcohol R'OH in which R' comprises an (optionally substituted) C_{7-30} cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof, and x and y are each in the range 1 - 3. The composition is useful as a curing agent for polyurethanes used in various applications.

WO 01/51536 A1

ORGANOMETALLIC COMPOSITIONS

This invention relates to organometallic compositions based on Group IVB metals and which are useful in polyisocyanate compositions especially compositions for binding lignocellulosic material.

5

The use of organic polyisocyanates as binders for lignocellulosic material in the manufacture of sheets or moulded bodies such as waferboard, chipboard, fibreboard and plywood is well known. In a typical process the organic polyisocyanate, optionally in the form of a solution, dispersion or aqueous emulsion, is applied to the lignocellulosic material which is then subjected to heat and
10 pressure. Isocyanates and polyisocyanates are also used in other applications in which it is necessary to effect curing of the compositions, e.g. in polyurethane coatings.

One suitable polyisocyanate composition is disclosed in PCT Application WO 97/17388. This composition comprises a Group IVB metal compound, preferably a titanium chelate, optionally in
15 combination with a compatibilising compound and/or conventional release agents. Although these compositions perform well as binders for lignocellulosic material and provide good release performance, it is desirable to develop a more economical composition which provides improved stability on storage before use, together with good curing properties and excellent bonding strength when applied to the lignocellulosic material.

20

US-A-5846897 discloses zirconium compounds with diketones or alkylacetoacetates which catalyse the isocyanate – hydroxy reaction having the chemical structure:
Me (X1, X2, X3, X4) wherein Me is zirconium (Zr) or hafnium (Hf) and X1, X2, X3, and X4, are the same or different and selected from the group consisting of a diketone and an alkylacetoacetate
25 having the structures: $R_1COCH_2COR_2$ and $R_1OCOCH_2COR_2$ wherein each of R_1 and R_2 is a branched or linear C1 -C20 hydrocarbon and at least one of X1, X2, X3, and X4 is a diketone with structure (II) wherein the total number of carbons in $R_1 + R_2$ is at least 4.

International Patent Application WO 00/02855 discloses that certain compounds of Group IVB
30 metals can be used to cure isocyanate and polyisocyanate compositions and these compositions are very stable on prolonged storage and economical when used for binding lignocellulosic material. The compounds disclosed are complexes of titanium, zirconium and/or hafnium and a acetoacetate ester in which the molar ratio of Ti or Hf to acetoacetate ester is in the range 1 : 2.5 to 1:10 or the molar ratio of Zr to acetoacetate ester is in the range 1 : 4.5 to 1 : 10 and said
35 acetoacetate ester is an ester of an alcohol containing 1 to 6 carbon atoms.

The physical properties of the materials used in this application are, of course an important factor in selecting appropriate compounds for use in curing the polyisocyanate compositions. One property which affects the handling and storage of the compounds is their flash point. It is desirable for the flash point to be relatively high for safety reasons whilst the melting point should
5 be low enough for the material to be in liquid form under normal conditions for ease of handling.

It is an object of the present invention to provide an organometallic composition which is useful in the curing of polyisocyanate compositions and which has improved handling characteristics compared with the compositions of the prior art.

10

According to the invention, an organometallic composition comprises a complex of at least one orthoester of a metal having a formula $M(ROAcAc)_x(OR')_y$ in which

- (a) M is selected from the group consisting of titanium, zirconium and hafnium;
- (b) ROAcAc denotes an ester of an alcohol ROH, in which R comprises an (optionally
15 substituted) C_{1-30} cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof, with acetoacetic acid;
- (c) OR' is the residue of an alcohol R'OH in which R' comprises an (optionally substituted) C_{7-30} cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof, and
- (d) x and y are each in the range 1 – 3 and $x + y = 4$.

20

M is selected from the group consisting of titanium, zirconium and hafnium and the composition may comprise a mixture of these metals.

- The titanium, zirconium or hafnium composition of the invention is described herein as a
25 "complex". It is believed that some of the acetoacetate ester will be chemically bound to the metal (Ti, Zr and/or Hf) but some may be present as "free" ester. The exact proportions which are bound and free will depend partly upon the exact molar ratios present in the complex and which metal, or metals, are used, but it has been shown that the "free" ester does influence the properties, particularly the stability on storage of polyisocyanate compositions containing the complexes.
- 30 Preferably the composition contains at least 0.5 moles of free ester per mole of metal, e.g. 0.5 – 10 moles, more preferably 1 – 5 moles free ester per mole of metal.

- The molar ratio of titanium to total acetoacetate ester (i.e. free ester + complexed ester) in the composition is preferably in the range 1 : 2.5 to 1 : 10. When the metal is titanium, the molar ratio
35 is preferably in the range 1 : 2.5 to 1 : 8 and more preferably in the range 1 : 3 to 1 : 6. When the

metal is hafnium or zirconium, the molar ratio is preferably 1 : 4 to 1 : 10 and more preferably 1 : 4 to 1 : 8, hafnium or zirconium to total acetoacetate ester. For all metals mentioned, the complexes of the invention contain at least one alkoxide group and at least one acetoacetate ester so that x and y are each in the range 1 – 3 and the total of x + y is 4. When the metal is titanium, both x and y are preferably 2.

Preferably, the complex is a complex of at least one of titanium and zirconium and most preferably M is titanium.

10 R comprises an (optionally substituted) C_{1-30} cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof. The preferred acetoacetate esters for preparing the complexes include ethyl acetoacetate, methyl acetoacetate, but esters of higher alcohols, e.g. C_{7-30} preferably C_{7-12} may be used, e.g. cetyl acetoacetate. The use of esters of higher alcohols is particularly preferred when the complex is to be used in applications in which it is subjected to
15 elevated temperatures, e.g. above the boiling point of EtAcAc (b.p. = 181°C). It is not necessary that the acetoacetate esters are prepared by reacting the alcohol ROH with acetoacetic acid or a derivative thereof, since it is well known that esters may be made by other methods, e.g. by transesterification of another ester. Therefore the term "ester of an alcohol ROH in which R is an (optionally substituted) C_{1-30} alkyl group with acetoacetic acid" as used herein is not to be taken
20 to limit the ester to compounds made or obtainable by direct esterification of the acetoacetic acid with the alcohol. The complex can be prepared from more than one acetoacetate ester but preferably only one acetoacetate ester is present in the complex.

Preferred substituents on the R group, include halogens, especially bromine, chlorine or fluorine
25 atoms since these substituted groups may enhance fire retardancy properties.

The group R'O is an alkoxide group in which R' is a substituted or unsubstituted, C_{7-30} cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof. It has been found that selection of such a group, i.e. having at least 7 carbon atoms produces metal complexes
30 having desirable flash-point characteristics i.e. a flash point above 50 °C. In preferred complexes of the invention R' is a C_{8-12} alkyl group, e.g. 2-ethyl hexyl or other branched octyl species such as iso-octyl (2,4,4 trimethyl 1 pentanol) or mixed isomers of branched alkyl alcohol species such as the "Exxal™" products, e.g. Exxal 8, available from Exxon. Preferred complexes according to the invention include di(2-ethylhexyloxy)titanium bis(ethylacetoacetate) which has a flash point of
35 about 68 °C and di(2,4,4-trimethyl-1-pentyloxy)titanium bis(ethylacetoacetate) which has a flash

point of about 58 °C, preferably in the presence of free acetoacetate ester. Preferred substituents on the R' group, include halogens, especially bromine, chlorine or fluorine atoms since these substituted groups may enhance fire retardancy properties.

- 5 Typically, the complexes of titanium, zirconium or hafnium of the invention are prepared by trans-
esterification by R'OH of titanium, zirconium or hafnium compounds having the general formula
 $M(OR'')_y (ROAcAc)_x$ in which M is Ti, Zr or Hf and R'' is a substituted or unsubstituted, cyclic,
branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or mixtures thereof. For clarity, these
compounds will be referred to hereinafter as "pre-complexes" Preferably, R'' contains up to 6
10 carbon atoms and, more preferably, up to 4 carbon atoms. Generally, both OR'' groups will be
identical but alkoxides derived from a mixture of alcohols can be used and mixtures of alkoxides
can be employed when more than one metal is present in the complex. In preferred pre-
complexes, R'' has less than 7 carbon atoms, esp 1 - 4 C atoms and is preferably methyl, ethyl,
iso-propyl, n-propyl, t-butyl or n-butyl. We have found that preparation of compounds of formula
15 $M(OR')_4$ when R' has > 7 carbon atoms is very difficult and that it is therefore not practical to
prepare the desired compounds by the apparently more obvious route of mixing together $M(OR')_4$
with an acetoacetate ester, and removing R'OH.

- The pre-complexes, $M(OR'')_y (ROAcAc)_x$, which form the starting material for the above-described
20 preparation are conveniently prepared from $M(OR'')_4$ where, as before, R'' is a substituted or
unsubstituted, cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or mixtures thereof.
Preferably, R'' contains up to 6 carbon atoms and, more preferably, up to 4 carbon atoms.
Generally, all four OR'' groups will be identical but alkoxides derived from a mixture of alcohols can
be used and mixtures of alkoxides can be employed when more than one metal is present in the
25 complex. In preferred starting material compounds, R'' is iso-propyl, n-propyl, t-butyl or n-butyl.

- Suitable alkoxides include tetramethoxytitanium, tetra-ethoxytitanium, tetra-isopropoxytitanium,
tetra-n-propoxytitanium, tetrabutoxytitanium, tetrapropoxyzirconium, tetrabutoxyzirconium, tetra-
n-propoxyhafnium and tetra-n-butoxyhafnium. The pre-complexes can be readily prepared by
30 mixing, for example, a metal alkoxide or condensed alkoxide with an appropriate amount of
acetoacetate ester. Alcohol from the alkoxide will be displaced by the acetoacetate ester and,
preferably, the displaced alcohol is removed by, for example, distillation. In a preferred method, 2
moles of acetoacetate ester per atom of Ti or 4 moles of acetoacetate ester per atom of Zr or Hf
are added to an alkoxide or condensed alkoxide and the displaced alcohol is removed by
35 distillation.

Alternatively, the pre-complexes can be prepared from condensed alkoxides of titanium, zirconium or hafnium. These compounds can be represented by the general formula $R''O[M(OR)_2O]_zR''$, wherein M and R'' have the same meaning as discussed above and z is an integer. Generally, these condensed alkoxides consist of a mixture containing compounds of the above formula where z is an integer which may have a range of values. Preferably z has an average value in the range 2 to 16 and, more preferably, in the range 2 to 8. A condensed alkoxide is usually prepared by the controlled addition of water to an alkoxide, followed by removal of alcohol which is displaced. Suitable condensed alkoxides include the compounds known as polybutyl titanate, polybutyl zirconate and polyisopropyl titanate. Complexes of condensed alkoxides can also be prepared by forming a complex of an acetoacetate ester with an alkoxide, adding water to the complex and removing any by-product alcohol.

Alternatively, when an organometallic composition according to the invention is used in a polyisocyanate composition and it is desired to have free acetoacetate ester present, a product can be prepared according to the method outlined above and this can be mixed with a polyisocyanate. Any additional acetoacetate ester required can then be added to the polyisocyanate before or after the titanium, zirconium or hafnium compound has been added. This effectively results in the preparation of an organometallic composition *in situ* in the polyisocyanate composition. Other methods of preparing the composition of the invention will be apparent to a person skilled in this art.

The organometallic complexes of the invention are particularly useful as curing agents in polyisocyanate compositions and compositions suitable for use with the organometallic compositions of the present invention may be any organic polyisocyanate compound or mixture of organic polyisocyanate compounds, provided said compounds have at least 2 isocyanate groups. Organic polyisocyanates include diisocyanates, particularly aromatic diisocyanates, and isocyanates of higher functionality.

Examples of organic polyisocyanates for which the organometallic complexes of the present invention are useful curing agents include aliphatic isocyanates such as hexamethylene diisocyanate; and aromatic isocyanates such as m- and p-phenylene diisocyanate, tolylene-2,4- and tolylene-2,6-diisocyanate, diphenylmethane-4,4'-diisocyanate, chlorophenylene-2,4-diisocyanate, naphthylene-1,5-diisocyanate, diphenylene-4,4'-diisocyanate, 4,4'-diisocyanate-3,3'-dimethyl-diphenyl, 3-methyldiphenylmethane-4,4'-diisocyanate and diphenyl ether diisocyanate;

and cycloaliphatic diisocyanates such as cyclohexane-2,4- and -2,3-diisocyanate, 1-methylcyclohexyl-2,4- and -2,6-diisocyanate and mixtures thereof and bis-(isocyanatocyclohexyl)methane and triisocyanates such as 2,4,6-triisocyanatotoluene and 2,4,4-tri-isocyanatodiphenylether.

5

Modified polyisocyanates containing isocyanurate, carbodiimide or uretonimine groups may be employed in conjunction with the organometallic complexes of the invention as well. Further blocked polyisocyanates, like the reaction product of a phenol or an oxime and a polyisocyanate, may be used, having a deblocking temperature below the temperature applied when using a

10 polyisocyanate composition.

The organic polyisocyanate useful with the organometallic composition of the invention may also be an isocyanate-ended prepolymer made by reacting an excess of a diisocyanate or higher functionality polyisocyanate with a polyol.

15

Water-emulsifiable organic polyisocyanates like those described in UK patent no. 1 444 933, in European patent publication no. 516 361 and in PCT patent publication no. 91/03082 can also be used.

20 Mixtures of isocyanates may be used in conjunction with the organometallic composition of the invention, for example a mixture of tolylene diisocyanate isomers such as the commercially available mixtures of 2,4- and 2,6-isomers and also the mixture of di- and higher polyisocyanates. Polyisocyanate mixtures may optionally contain monofunctional isocyanates such as p-ethyl phenylisocyanate.

25

Such mixtures are well-known in the art and include the crude phosgenation products containing methylene bridged polyphenyl polyisocyanates, including diisocyanate, triisocyanate and higher polyisocyanates together with any phosgenation by-products.

30 Preferred isocyanates to be used in conjunction with the organometallic complexes of the present invention are those wherein the isocyanate is an aromatic diisocyanate or polyisocyanate of higher functionality such as a pure diphenylmethane diisocyanate or a mixture of methylene bridged polyphenyl polyisocyanates containing diisocyanates, triisocyanates and higher functionality polyisocyanates.

35

Methylene bridged polyphenyl polyisocyanates are well known in the art. They are prepared by phosgenation of corresponding mixtures of polyamines. For convenience, polymeric mixtures of methylene bridged polyphenyl polyisocyanates containing diisocyanate, triisocyanate and higher functionality polyisocyanates are referred to hereinafter as polymeric MDI. Polyisocyanates
5 suitable for use with the organometallic complexes of the invention include SUPRASEC™ DNR, SUPRASEC™ 2185, RUBINATE™ M and RUBINATE™ 1840, all available from Huntsman ICI Polyurethanes..

Preferably the polyisocyanate is liquid at room temperature.

10

Conventional release agents can be added to or used in combination with a polyisocyanate composition containing a titanium, zirconium or hafnium complex according to the present invention.

15 In such compositions the conventional release agent is present in an amount varying between 0.2 and 10 %, preferably between 0.5 and 6 % and most preferably between 1 and 3 % by weight based on the polyisocyanate whereas the titanium, zirconium or hafnium complex is preferably present in an amount varying between 0.2 and 4 %, most preferably between 0.2 and 2 % by weight based on the polyisocyanate.

20

Examples of conventional release agents include polysiloxanes, saturated or unsaturated fatty acids (such as oleic acid) or fatty acid amides or fatty acid esters and polyolefin waxes.

Preferred conventional release agents to be used in polyisocyanate compositions containing the
25 organometallic complexes according to the present invention are polyolefin waxes or mixtures of polyolefin waxes, especially functionalised polyolefin waxes, which are dispersible in an aqueous medium to form an aqueous emulsion. More preferably, the polyolefin waxes are selected from oxidised polyethylene waxes and oxidised polypropylene waxes.

30 A preferred method for using the release agent is to apply the emulsion to the surface of the polyisocyanate treated lignocellulosic material or to the press metal surface prior to hot pressing the combination.

When used, an aqueous emulsion of the polyolefin wax should normally contain a sufficient
35 amount of the polyolefin wax to provide a coverage of about 0.01 to about 1, and preferably about

0.02 to about 0.5 mg of the polyolefin wax per cm² of lignocellulosic material or press metal surface. Generally, lower levels of polyolefin wax are preferred as they are more cost effective. When taking the emulsifiers into account, the aqueous emulsions will usually contain about 0.2 to about 10 %, preferably about 0.3 to about 5 % by weight of total solids. The emulsions are usually
5 prepared at 30 to 40 % total solids, transported to the point of use and then diluted with water to the desired concentration.

It has been found that the polyolefin wax emulsion, when used in combination with polyisocyanate compositions containing organometallic compositions of the present invention, may be usefully
10 applied to the lignocellulosic material or press metal surface in an amount equivalent to 8 to 14 mg per cm².

A particularly preferred polyethylene wax emulsion which can be used in a process in combination with an organometallic composition of the present invention in combination with a polyisocyanate
15 is Rubilon™ 603 or Rubilon™ 605, both available from Imperial Chemical Industries.

A particularly preferred polypropylene wax emulsion which can be used in a process in combination with an organometallic composition of the present invention in combination with a polyisocyanate is ME 42040 available from Michelman Inc. of Cincinnati, Ohio.

20 In order to further improve the storage stability of a polyisocyanate composition containing an organometallic composition of the present invention a diluent may be added to the composition. Suitable diluents include plasticizers of the type mentioned in "Taschenbuch der Kunststoff-Additive", Ed. by R. Gachter and H. Muller, Carl Hanser Verlag Munchen, third edition, 1989.
25 Preferred diluents are phthalates, aliphatic carboxylates, fatty acid esters, linseed oil and soybean oil. A particularly preferred diluent is Priolube 1403 available from Unichema being methylolate. These diluents are added in amounts of from 1 to 40 parts by weight per 100 parts by weight of polyisocyanate and preferably in amounts of from 1 to 15 parts by weight per 100 parts by weight of polyisocyanate.

30 A composition containing an organometallic composition of the present invention and a polyisocyanate may further comprise conventional additives such as flame retardants, lignocellulosic preserving agents, fungicides, waxes, sizing agents, fillers, surfactants; thixotropic agents and other binders like formaldehyde condensate adhesive resins and lignin (optionally in
35 combination with a lignin solvent such as described in PCT Patent Application No. EP96/00924).

A particularly preferred additive to be used in a polyisocyanate composition containing an organometallic composition of the present invention is a coupling agent such as an organofunctional silane (for example, Dynasylan AMEO, available from Huels). Adding such a coupling agent to the polyisocyanate composition leads to improved board properties. The organo-
5 functional silane coupling agents are used in amounts ranging from 0.01 to 3 %, preferably from 0.1 to 2 % by weight based on the polyisocyanate.

The organometallic composition of present invention can be used in a process for preparing
10 lignocellulosic bodies by bringing lignocellulosic parts into contact with a polyisocyanate composition containing the organometallic composition of the present invention and pressing this combination.

A typical process comprises the steps of
15 a) bringing said lignocellulosic material in contact with a polyisocyanate composition containing an organometallic composition of the present invention and,
b) subsequently allowing said material to bind.

The lignocellulosic bodies are prepared by bringing the lignocellulosic parts into contact with a
20 polyisocyanate composition by means such as mixing, spraying and/or spreading the composition with/onto the lignocellulosic parts and by pressing the combination of the polyisocyanate composition and the lignocellulosic parts, preferably by hot-pressing, normally at 150° C to 250°C and 2 to 6 MPa specific pressure. Such binding processes are commonly known in the art.

25 In wafer-board manufacture the lignocellulosic material and the polyisocyanate composition may be conveniently mixed by spraying the present polyisocyanate composition on the lignocellulosic material while it is being agitated.

As described hereinbefore, in a preferred process, a release agent, which is preferably an
30 aqueous emulsion of a polyolefin wax, is applied to the surface of the polyisocyanate treated lignocellulosic material or to the press metal surface prior to hot pressing the combination.

The lignocellulosic material after treatment with the polyisocyanate composition containing an organometallic composition according to the invention is placed on caul plates made of aluminium
35 or steel which serve to carry the furnish into the press where it is compressed to the desired extent

usually at a temperature between 150° C and 250° C.

While the process is particularly suitable for the manufacture of wafer-board known extensively as oriented strand board and will be largely used for such manufacture, the process may not be
5 regarded as limited in this respect and can also be used in the manufacture of medium density fibreboard, particle board (also known as chipboard) and plywood.

Thus the lignocellulosic material used can include wood strands, wood-chips, wood fibres, shavings, veneers, wood wool, cork, bark, sawdust and like waste products of the wood working
10 industry as well as other materials having a lignocellulosic basis such as paper, bagasse, straw, flax, sisal, hemp, rushes, reeds, rice hulls, husks, grass, nutshells and the like. Additionally, there may be mixed with the lignocellulosic materials other particulate or fibrous materials such as ground foam waste (for example, ground polyurethane foam waste), mineral fillers, glass fibre, mica, rubber, textile waste such as
15 plastic fibres and fabrics.

When the polyisocyanate composition containing the organometallic composition of the invention is applied to the lignocellulosic material, the weight-ratio of polyisocyanate/lignocellulosic material will vary depending on the bulk density of the lignocellulosic material employed. Therefore, the
20 polyisocyanate compositions may be applied in such amounts to give a weight ratio of polyisocyanate/lignocellulosic material in the range of 0.1 : 99.9 to 20 : 80 and preferably in the range of 0.5 : 99.5 to 10 : 90.

If desired, other conventional binding agents, such as formaldehyde condensate adhesive resins,
25 may be used in conjunction with the polyisocyanate composition containing the organometallic composition.

More detailed descriptions of methods of manufacturing wafer-board and similar products based on lignocellulosic material are available in the prior art. The techniques and equipment
30 conventionally used can be adapted for use with polyisocyanate compositions containing organometallic compositions of the present invention.

Polyisocyanate compositions containing organometallic compositions of the present invention are extremely effective in minimising unwanted adhesion to caul plates, press plates and other
35 surfaces with which the treated lignocellulosic material may come into contact. Their storage

stability and release performance is improved compared to polyisocyanate compositions of the prior art, as well as the obtained board properties. Also the flash point of the complexes of the present invention are relatively high, enabling them to be stored and handled more easily than materials having lower flash points.

5

The sheets and moulded bodies produced from the polyisocyanate compositions containing organometallic compositions of the present invention have excellent mechanical properties and they may be used in any of the situations where such articles are customarily used.

- 10 The organometallic compositions of the invention are also useful in other applications in which it is desired to effect curing of isocyanate groups in a polyurethane. Such other applications include coatings, e.g. decorative and industrial coatings for protection of wood, metals, plastics, glass, ceramics and other surfaces, including coatings subjected to heat. For use in higher temperature applications it may be advantageous to use an acetoacetate ester of an alcohol which has a high
- 15 boiling point, e.g. above 200°C, such as an acetoacetate ester of an alcohol having at least 7 carbon atoms. Other applications include the manufacture of composite materials in which polyurethane binders are used, such as oriented strand board (OSB), medium-density fibreboard (MDF) or plywood. Still further applications may be found in composites, adhesives and foams and thermoplastic polyurethanes for use in automotive applications or footwear.

20

The invention is illustrated but not limited by the following examples.

EXAMPLE 1 Preparation of precomplex material A

- A reactor was charged with tetraisopropyl titanate (1400 kg, Tilcom® TIPT from ICI Vertec). Ethylacetoacetate (EtAcAc) (1282 kg) was then added with stirring. The resulting product was a pale red liquid. The displaced alcohol (580 kg, isopropanol) was then removed by evaporation to leave a red liquid, precomplex A (2090 kg), di(2-propyloxy)titanium bis(ethylacetoacetate).
- 25

EXAMPLE 2 Preparation of complex according to the invention

- 30 Precomplex A (423.88 g) was stirred with 260.41 g of 2-ethyl hexanol and then distilled under vacuum to remove isopropanol until a constant weight was obtained. The product was di(2-ethylhexyloxy)titanium bis(ethylacetoacetate). 325 g of Et AcAc was added and the resulting product was a red mobile liquid, having a flash point of 68°C as measured by the Gallenkamp Auto Flash AF3 using the method described in the Gallenkamp manual DET 284-488E issue III.

35

EXAMPLE 3 Preparation of complex according to the invention

The method described in Example 2 was followed but 260.7 g of iso octanol (2,4,4 trimethyl 1 pentanol) was substituted for the 2-ethyl hexanol. The resulting product , di(2,4,4-trimethyl-1-pentyloxy)titanium bis(ethylacetoacetate) with about 2.5 moles excess Et AcAc was a red mobile liquid, having a flash point of 58 °C.

EXAMPLE 4 Comparison

Example 2 was repeated using 148 g of iso-butanol instead of 2-ethyl hexanol to produce di(2,2-dimethyl-1-ethyloxy)titanium bis(ethylacetoacetate) . The resulting product was a clear orange/red mobile liquid having a flash point of 56 °C.

EXAMPLE 5 Comparison

A reactor was charged with 283 g tetra(n-propyl)titanate. EtAcAc (260 g) was then added with stirring. The displaced alcohol (139 g, n-propanol) was then removed by evaporation until a constant weight was obtained to leave a yellow-orange liquid, di(n-propyloxy)titanium bis(ethylacetoacetate) . 325 g of Et AcAc was added and the resulting product was a clear orange/red liquid, having a flash point of 46 °C.

EXAMPLE 6 Comparison

325 g of Et AcAc was added to 426 g of precomplex A and the resulting product was a clear orange/red liquid, having a flash point of 49 °C.

EXAMPLE 7 Comparison of viscosity of polyisocyanate containing complexes according to the invention

The products were evaluated by preparing a number of compositions comprising 100 g by weight of polyisocyanate (SUPRASEC DNR, available from Huntsman ICI Polyurethanes) and the indicated amount of the samples prepared in Examples 2 - 6. Each composition contained the same concentration of the complex. The compositions were then stored at 45 °C and the viscosity tested by means of a Brookfield DV-II Programmable Viscometer (following the Operating instructions found in the Brookfield Operating Instructions Manual No M/97-164-B299) at various intervals up to 85 days. The results are shown in the Table show that the titanates which raise the viscosity of the polyisocyanates least are those of Examples 2, 3 and 5, but of these only those of the invention have a flash point which is > 50 °C.

Complex	Viscosity (cP) at 25°C					
	Flash pt (°C)	weight added (g)	Day 0	Day 21	Day 54	Day 85
Example 2	68.0000	0.6300	220.000 0	366.000 0	518.0000	828.000 0
Example 3	58.0000	0.6400	220.000 0	430.000 0	564.0000	774.000 0
Example 4 (comp)	56.0000	0.5500	220.000 0	376.000 0	568.0000	1044.00 00
Example 5 (comp)	46.0000	0.5100	220.000 0	416.000 0	520.0000	908.000 0
Example 6 (comp)	49.0000	0.5300	220.000 0	364.000 0	580.0000	1296.00 00

CLAIMS

1. An organometallic composition comprising a complex of at least one orthoester of a metal having a formula $M(\text{ROAcAc})_x (\text{OR}')_y$ in which
 - (a) M is selected from the group consisting of titanium, zirconium and hafnium;
 - (b) ROAcAc denotes an ester of an alcohol ROH, in which R comprises an (optionally substituted) C_{1-30} cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof, with acetoacetic acid;
 - (c) OR' is the residue of an alcohol R'OH in which R' comprises an (optionally substituted) C_{7-30} cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof, and
 - (d) x and y are each in the range 1 – 3 and $x + y = 4$.
2. An organometallic composition as claimed in claim 1, wherein R comprises an optionally substituted $\text{C}_7 - \text{C}_{30}$ cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof.
3. An organometallic composition as claimed in claim 1, wherein R comprises an optionally substituted $\text{C}_1 - \text{C}_6$ cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof.
4. An organometallic composition as claimed in any of the preceding claims, wherein R' comprises an optionally substituted $\text{C}_7 - \text{C}_{18}$ cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof.
5. An organometallic composition as claimed in claim 4, wherein R' comprises an optionally substituted $\text{C}_7 - \text{C}_{12}$ alkyl group.
6. An organometallic composition as claimed in any of the preceding claims, wherein R' and/or R contains at least one bromine, chlorine or fluorine atom.
7. An organometallic composition as claimed in any of the preceding claims, wherein M is titanium and the molar ratio of titanium to acetoacetate ester in the composition is in the range 1 : 2.5 to 1 : 10.
8. An organometallic composition as claimed in any of claims 1 - 6, wherein M is either hafnium or zirconium and the molar ratio of M to acetoacetate ester in the composition is in the range 1 :

4 to 1 : 10.

9. An organometallic composition as claimed in any of the preceding claims, wherein the composition comprises free acetoacetate ester.
10. An organometallic composition as claimed in claim 9, wherein said free acetoacetate ester is present in an amount to provide 0.5 – 10 moles free ester per mole of metal.
11. An organometallic composition as claimed in claim 10, wherein said free acetoacetate ester is present in an amount to provide 1 - 5 moles free ester per mole of metal.
12. An organometallic composition as claimed in any of the preceding claims, which is prepared by trans-esterification by R'OH of titanium, zirconium or hafnium compounds having the general formula $M(OR'')_2(ROAcAc)_x$ in which M is Ti, Zr or Hf and R'' is a substituted or unsubstituted, cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or mixtures thereof.
13. An organometallic composition as claimed in claim 12, wherein R'' comprises methyl, ethyl, isopropyl, n-propyl, iso-butyl or n-butyl.
14. An organometallic composition as claimed in any of the preceding claims which has a flash point greater than 50°C
15. A method of making an organometallic composition as claimed in claim 1 comprising the steps of:
- a) mixing together a metal tetra-alkoxide, $M(OR'')_4$ with an acetoacetate ester, ROAcAc, in which R and R'' are each selected from a (substituted or unsubstituted) cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or mixtures thereof and M is selected from titanium, hafnium or zirconium, such that at least 2 moles of ROAcAc is present in the mixture for each mole of $M(OR'')_4$
 - b) removing from the mixture the alcohol R''OH formed during the reaction;
 - c) and then adding to said mixture an alcohol R'OH in which R' comprises an (optionally substituted) C₇₋₃₀ cyclic, branched or linear, alkyl, alkenyl, aryl or alkyl-aryl group or a mixture thereof ;
 - d) removing from the mixture the alcohol R''OH formed during the reaction;
- and optionally

e) adding a further quantity of ROAcAc such that when M is titanium the molar ratio of titanium to total acetoacetate ester in the composition is in the range 1 : 2.5 to 1 : 10 and when M is either hafnium or zirconium the molar ratio of M to total acetoacetate ester in the composition is in the range 1 : 4 to 1 : 10.

16. Use of an organometallic composition as claimed in any of claims 1 - 11 as a curing agent for isocyanate compositions.

17. Use of an organometallic composition as claimed in claim 15 as a curing agent in coatings, composite materials, adhesives, foams and thermoplastic polyurethanes.

18. A curable mixture comprising an organic isocyanate compound or mixture of organic isocyanate compounds and an organometallic composition as claimed in any of claims 1 - 15.

19. A curable mixture as claimed in claim 18, wherein said isocyanate compound is an aliphatic or aromatic diisocyanate, a modified polyisocyanate containing isocyanurate, carbodiimide or uretonimine groups, an isocyanate-ended prepolymer made by reacting an excess of a diisocyanate or higher functionality polyisocyanate with a polyol; a water-emulsifiable organic polyisocyanate or a mixture of two or more of the aforementioned polyisocyanates.

20. A curable mixture as claimed in claim 19, wherein said isocyanate is selected from hexamethylene diisocyanate, m- and/or p-phenylene diisocyanate, tolylene-2,4- or tolylene-2,6-diisocyanate, diphenylmethane-4,4'-diisocyanate, chlorophenylene-2,4-diisocyanate, naphthylene-1,5-diisocyanate, diphenylene-4,4'-diisocyanate, 4,4'-diisocyanate-3,3'-dimethyldiphenyl, 3-methyldiphenylmethane-4,4'-diisocyanate and diphenyl ether diisocyanate, cyclohexane-2,4- and/or -2,3-diisocyanate, 1-methylcyclohexyl-2,4- and/or -2,6-diisocyanate, bis-(isocyanatocyclohexyl)methane, 2,4,6-triisocyanatotoluene and 2,4,4-triisocyanatodiphenylether.

21. A lignocellulosic body comprising a lignocellulosic material, and a polyisocyanate composition containing an organometallic composition as claimed in any of claims 1 - 15.

21. A process for the preparation of a lignocellulosic body comprising the steps of
a) bringing a lignocellulosic material in contact with a polyisocyanate composition containing an organometallic composition as claimed in any of claims 1 - 15, and
b) subsequently allowing said material to bind.

INTERNATIONAL SEARCH REPORT

International Application No

B 00/04853

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08G18/22 C08G18/64 C07F7/00 B01J31/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08G C07F B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category * Citation of document, with indication, where appropriate, of the relevant passages

Relevant to claim No.

A US 4 478 755 A (ROBBINS GORDON B)
23 October 1984 (1984-10-23)
examples 1,2E; table II
claim 1

A US 5 646 200 A (DUNCAN ROBERT HUME)
8 July 1997 (1997-07-08)
column 1, line 33 -column 2, line 16
claims 1,6,12; example 1

A WO 97 17388 A (ICI PLC)
15 May 1997 (1997-05-15)
cited in the application
page 1, line 41 -page 3, line 24
claims 1,4-9
examples 7-10

1,7,15

1,8,9,15

1,2,7,
15-19,21

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

23 March 2001

03/04/2001

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Neugebauer, U

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT 00/04853

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4478755	A	23-10-1984	NONE	
US 5646200	A	08-07-1997	AT 188985 T	15-02-2000
			AU 681503 B	28-08-1997
			AU 2032895 A	04-01-1996
			BR 9502639 A	05-03-1996
			CA 2150283 A	23-12-1995
			CN 1125242 A,B	26-06-1996
			DE 69514575 D	24-02-2000
			DE 69514575 T	15-06-2000
			DK 688837 T	13-06-2000
			EP 0688837 A	27-12-1995
			ES 2141301 T	16-03-2000
			FI 953076 A	23-12-1995
			GB 2290545 A,B	03-01-1996
			JP 8048925 A	20-02-1996
			NO 952457 A	27-12-1995
			PT 688837 T	28-04-2000
			ZA 9505178 A	31-01-1996
WO 9717388	A	15-05-1997	AU 7298096 A	29-05-1997
			BR 9611385 A	26-01-1999
			CN 1201469 A	09-12-1998
			CZ 9801369 A	12-08-1998
			EP 0859805 A	26-08-1998
			JP 11514690 T	14-12-1999
			NO 982043 A	06-07-1998
			PL 326551 A	28-09-1998
			SK 59098 A	09-09-1998
			TR 9800806 T	21-08-1998

THIS PAGE BLANK (USPTO)